

WATER METALLIC

Descripción

Fecha de Revisión: 7-15-13

Sistema de tintas metálicas a base agua.

Aplicación

Prensa: Aplicación Flexográfica con rasqueta y dos rollos
Anilox: 4.5 BCM o mejor
Sustrato: Brilloso
Velocidad típica de Prensa: 125 - 400 Pies / minuto
Notas: No usar aditivo Clean Print o ninguna solución para subir el pH.
Este sistema no puede ser mezclado y/o dar tono con base agua como típicamente se hace con sistemas de tintas pigmentadas.

Almacenamiento y Manejo

Fecha de expiración máxima de 6 meses de la fecha de fabricación. Después de abrir, usar lo antes posible. Proteger de congelamiento, calor y exposición al sol. Es posible el incremento de viscosidad si se almacena incorrectamente o por periodos largos de tiempo. Evitar la mezcla con otros barnices o agua al lavado.

Propiedades Típicas

pH 8.2 – 8.8
Viscosidad: 40 - 45" (3 Zahn)

The information and data contained herein are believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since ACTEGA WIT, Inc. cannot know all of the uses to which its products may be put, or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose. You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires government approval or clearance you must obtain it. ACTEGA WIT, Inc. warrants only that its products will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. The user's exclusive remedy and ACTEGA WIT, Inc.'s sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. ACTEGA WIT, Inc. will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.

@ Copyright 2013 ACTEGA WIT, Inc.

ACTEGA WIT, Inc. 125 Technology Dr. Lincolnton, NC 28092 USA Phone 704.735.8282 Fax 704.732.6333

A member of  **ALTANA**

Linea de Producto

Water Metallic

WML008871	871 Gold	WML008875	875 Gold
WML008872	872 Gold	WML008876	876 Gold
WML008873	873 Gold	WML008877	877 Silver
WML008874	874 Gold		

Igualación de colores especiales sobre su solicitud

Aditivos

Agua	Reduce viscosidad y fuerza en el color (incremento de 2-3% únicamente)
Propylene Glycol	Reduce el nivel de secado (incremento de 1-3% únicamente)

Desecho

Tintas y barnices incluyendo lavado de prensa no debe de ser desechado en ningún sistema de drenaje sin antes revisar las regulaciones locales. Desecho apropiado puede involucrar tratamiento en planta o el ser removido por un agente de desechos autorizado.

Requerimientos de Regulación

Hoja con el Material de Seguridad (MSDS) será entregada con las cargas de los productos y/o solicitadas.

Datos con calidad de Aire disponibles a solicitud.

Sistema de Identificación de Materiales Peligrosos usado para todas las etiquetas.

The information and data contained herein are believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since ACTEGA WIT, Inc. cannot know all of the uses to which its products may be put, or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose. You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires government approval or clearance you must obtain it. ACTEGA WIT, Inc. warrants only that its products will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. The user's exclusive remedy and ACTEGA WIT, Inc.'s sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. ACTEGA WIT, Inc. will not be liable for incidental or consequential damages of any kind. Suggestions of uses should not be taken as inducements to infringe any patents.

@ Copyright 2013 ACTEGA WIT, Inc.

ACTEGA WIT, Inc. 125 Technology Dr. Lincolnton, NC 28092 USA Phone 704.735.8282 Fax 704.732.6333

A member of 