



Kodak

Flexcel SRC

Flexographic Plates

Outstanding performance for all corrugated applications

Kodak Flexcel SRC Flexographic Plates are low-durometer photopolymer plates ideal for halftone reproduction on coarse board. The plate's surface conforms uniformly to the printing substrate, providing smooth ink laydown and consistent tonal reproduction. The tack-free plate surface facilitates increased print quality and reduced press downtime throughout the life of the plate.

Versatility

Flexcel SRC Plates are designed to print on corrugated board. Because the plates are compatible with a wide variety of inks, including water-based, solvent-based, UV-cured and cationic inks, Flexcel SRC Plates are ideal for any job.

Speed and ease of use

Flexcel SRC Plates improve productivity with very fast imaging and processing speeds, a wide exposure latitude and short drying times. In addition, the extreme flexibility of the plates allows for fast and faultless mounting. High resistance to ozone, wear and abrasion and a long shelf life make Flexcel SRC Plates ideal for repeat jobs.

Complete solution for packaging

Kodak offers a full range of dependable products for packaging print operations. The Kodak Flexcel SRX System joins Kodak's portfolio of prepress, lithographic and proofing products for packaging. You can experience the benefits of an efficient, complete system from one supplier and realize consistent results, not only from run to run, but also from location to location, anywhere in the world.

Kodak Flexcel SRC Flexographic Plates

FLEXOGRAPHIC PLATES

Technical specifications

Plate thickness	2.84mm / 0.112", 3.18mm / 0.125", 3.94mm / 0.155", 4.32mm / 0.170", 4.70mm / 0.185", 5.00mm / 0.197", 5.50mm / 0.217", 6.00mm / 0.236", 6.35mm / 0.250", 7.00mm / 0.276"		
Resolution	3% to 95% @ 133 lpi		
Isolated dot reproduction	150 - 200µm		
Fine line reproduction	100µm		
Plate hardness Shore A	SRC 2.84mm / 0.112": 39 SRC 3.18mm / 0.125": 37 SRC 3.94mm / 0.155": 35 SRC 4.32mm / 0.170": 37	SRC 4.70mm / 0.185": 37 SRC 5.00mm / 0.197": 36 SRC 5.50mm / 0.217": 36 SRC 6.00mm / 0.236": 36	SRC 6.35mm / 0.250": 36 SRC 7.00mm / 0.276": 35
Wash-out solution	Compatible with most wash-out solvents Recommended wash-out solvent temperature: 20°C - 35°C (68°F - 95°F)		
Ink compatibility	Aqueous, solvent-based, UV-cured and cationic inks		
Storage and handling	Unopened plate packs should be stored flat and away from excessive cold, heat and humidity. Use in a controlled environment of 10°C - 25°C (50°F - 77°F) and 40 - 55% RH.		

Processing steps

Times/Values

Plate thickness	2.84mm / 0.112"	3.18mm / 0.125"	3.94mm / 0.155"	4.32mm / 0.170"	4.70mm / 0.185"
Relief depth	1.4mm / 0.055"	1.6mm / 0.063"	1.9mm / 0.075"	2.2mm / 0.087"	2.2mm / 0.087"
Back exposure time / seconds	250mj/cm ² 40 sec	400mj/cm ² 60 sec	600mj/cm ² 90 sec	800mj/cm ² 120 sec	1,000mj/cm ² 150 sec
Main exposure time / minutes	3,500mj/cm ² 8 min	3,500mj/cm ² 8 min	3,500mj/cm ² 8 min	4,000mj/cm ² 10 min	4,000mj/cm ² 10 min
Wash-out	6 min	6 min	6 min	10 min	10 min
Drying, 50°-60°C (122°-140°F)	120 min	120 min	120 min	120 min	120 min
Finishing UVC	2,500mj/cm ² 8 min	2,500mj/cm ² 8 min	2,500mj/cm ² 8 min	2,500mj/cm ² 8 min	2,500mj/cm ² 8 min
Post exposure UVA	4,000mj/cm ² 10 min	4,000mj/cm ² 10 min	4,500mj/cm ² 11 min	4,500mj/cm ² 11 min	4,500mj/cm ² 11 min
Plate thickness	5.00mm / 0.197"	5.50mm / 0.217"	6.00mm / 0.236"	6.35mm / 0.250"	7.00mm / 0.276"
Relief depth	2.3mm / 0.091"	2.3mm / 0.091"	2.5mm / 0.099"	2.5mm / 0.099"	2.7mm / 0.106"
Back exposure time / seconds	1,200mj/cm ² 180 sec	1,500mj/cm ² 230 sec	1,800mj/cm ² 270 sec	2,000mj/cm ² 300 sec	3,000mj/cm ² 450 sec
Main exposure time / minutes	4,000mj/cm ² 10 min	4,000mj/cm ² 10 min	4,000mj/cm ² 10 min	4,000mj/cm ² 10 min	4,000mj/cm ² 10 min
Wash-out	10 min	12 min	12 min	15 min	15 min
Drying, 50°-60°C (122°-140°F)	120 min	120 min	120 min	120 min	120 min
Finishing UVC	2,500mj/cm ² 8 min	2,500mj/cm ² 8 min	2,500mj/cm ² 8 min	2,500mj/cm ² 8 min	2,500mj/cm ² 8 min
Post exposure UVA	4,500mj/cm ² 11 min	5,000mj/cm ² 12 min	5,000mj/cm ² 12 min	5,000mj/cm ² 12 min	5,000mj/cm ² 12 min

To learn more about solutions from Kodak:
Visit www.kodak.com/go/packaging
Or in North America, call +1-866-563-2533

Produced using Kodak technology.

Eastman Kodak Company
343 State Street
Rochester, NY 14650 USA

©Kodak, 2010. Kodak, Flexcel and Premier are trademarks of Kodak.

Subject to technical change without notice.

U.PC.O16.0510.en.01 (K-508)

This document should be used as a guideline to producing Kodak Flexcel Flexographic Plates. Optimum exposure and development times will vary, depending on customer specific plate application and processing equipment.



It's time for you **AND** Kodak